

SPECIFICATION DATA SHEET - AXOLOTL PAINT Urethane Sealer **For the information of Specifiers and Trades**

Product description

Axolotl Urethane Sealer is a flexible, waterbased, protective clear satin finish. It is suited to higher traffic internal applications such as balustrades, floors, counters and furniture. Axolotl Urethane Sealer has minimal yellowing and is easy to recoat. Suitable for use over Axolotl Timberwash Interior, Chroma and Micaceous paints. Urethane sealer can also be used to seal raw timbers and concrete.

Suitable surfaces

Refer to specific treatment for the appropriate substrate

- 1 New timber
- 2 Previously painted with Axolotl Chroma or Metta paints
- 3 Bare concrete

Urethane Sealer substrate preparation

1. New timber

New timber must be dry and free of dirt oils and waxes or any other contaminants. Surface should be sanded with fine paper appropriate to the timber type and all dust should be thoroughly cleaned up. Nail holes should be filled with a appropriately coloured filler. Do not use linseed oil putty.

2. Previously painted with Axolotl Chroma or Metta paints

Axolotl Painted surfaces should be fully dry prior to applying Urethane Sealer.

3. Bare Concrete

Bare Concrete must be cured and dry and free of all dirt, dust laitance, efflorescence, oils, waxes or other contaminants. Apply one coat of Clear Acrylic Sealer by brush and roller or lambswool applicator in a thin even coat. Thinning with up to 5% water is recommended for absorbent cement surfaces. Allow to dry thoroughly before applying Axolotl Urethane Sealer.

Applying Urethane Sealer

Following the preparation of substrates (as previously outlined) Urethane Sealer is applied to a dry surface in a 2 - 3 coat system. Stir well before and during use ensuring that all material is mixed in from the bottom of tin. Apply an even coat by brush, lint free pad or roller. Avoid reworking the product. Work along full length of boards in groups of 3 or 4 at a time.

Drying time is typically 30 minutes to touch dry, allow at least 3 hours between each coat. Lightly sand between coats with 240 grit sandpaper. Full cure after 7 days.

Allow overnight drying before light traffic and 3 days before normal foot traffic.

Coverate is approximately 14m² per litre, allow 10 to 30% more for first coat over bare substrates.

General precautions

Paint application

Application over white and light colours may show some yellowing, it is recommended to test before proceeding. Suitable for internal applications only.

Temperature

Axolotl Urethane Sealer should not be applied where surface or air temperature is below 10°C or above 35°C. Excessively fast drying can occur if painting hot surfaces or in direct sunlight.

Initial protection

Adequate protection should be provided against rain and sub-zero temperatures for a period of not less than 24 hours after

Packaging

Axolotl Urethane Sealer is available in 1, 4, 10 & 15 litre containers.

NOTE FOR SPECIFIERS -

PLEASE ENSURE SPECIFICATION SHEET IS COPIED & ATTACHED TO TENDER DRAWINGS FOR THE REFERENCE OF ALL RELEVANT TRADES.

For further information, technical assistance or costing please contact:

| | |
|---------|---|
| Company | Axolotl Group Pty Ltd |
| Address | 6 / 73 Beauchamp Road, Matrville, N.S.W, 2036. |
| Phone | 02 9666 1207 |
| Email | info@axolotl.com |
| Website | www.axolotlpaint.com |