



Metal Paint Smooth

PRODUCT DATA

Description:

Quick air drying gloss finish to give a hard durable finish to metal substrates.

Provides good protection when used in conjunction with QAD Anti Corrosive Oxide Primer. Economical and easy to apply. Suitable for a wide variety of applications where speed and ease of application are required.

Area of use:

Internal/External/Industrial Structural Steel

Substrates:

Metal

Packing:

500 mls

Physical Constants:

Colour: Black, Blue, Green, Silver, White

Finish: Gloss

Volume solids: 45%

Theoretical spreading rate: 12 – 15 sq.metres per litre

Flash point: 23°C

Specific gravity: 1.10

Dry to touch: 15 minutes

Over-coating time: 4 Hours

**The theoretical spreading rate has been calculated for the stated volume solids and dry film thickness. A practical spreading rate will depend on the actual dry film thickness, the nature of the substrate, and the relevant consumption factor. The physical constants are subject to normal manufacturing tolerances.*

Application Details:

Application method: Brush / Conventional Spray / Airless Spray

Thinner: Xylene (T10009)

Cleaning of tools: Xylene (T10009)

Surface Condition:

The surface should be stable, firm, dry and free of dust, sand, loose old paint, dirt, grease and oil.

For additional guidance please contact your local Technical Sales Representative. Please check colour before use. If using multiple cans please check batch numbers are the same

SAFETY: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Material Safety Data Sheets and follow all local or national safety regulations.

Flag Paints Ltd. 8 Springfield Road, Burnham on Crouch, CM0 8UA, Tel:+44 1621 785173, Fax:+44 1621 785393

SAFETY: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Material Safety Data Sheets and follow all local or national safety regulations.

Flag Paints Ltd. 8 Springfield Road, Burnham on Crouch, CM0 8UA, Tel:+44 1621 785173, Fax:+44 1621 785393