

s59.2ms seat



Above, s59.2ms seat in powder coated mild steel with micro porous stain to wood.

description



Four leg seat for ground fixing or free standing in galvanized mild steel with polyester powder coating and treated hardwood laths.

dimensions

Length 1860mm, depth 629mm, height 819mm.

options



Unfinished timber or micro porous stain.
Chair and table options available.



s59.2ms Fixing Instructions



(for areas already paved, note this seat can be left free standing)

- 1 Attach the 4 no. fixing brackets with 8 no. M6 SS CSK bolts (provided).
- 2 Determine the location for the seat. Remove the pavers and excavate two holes at centres 1750mm.
- 3 Fill the holes with 35N20 concrete up to 15mm below the level of the underside of the pavers ensuring a good smooth surface finish.
- 4 Allow sufficient time for the concrete to set then apply a layer of dry sand/cement mix over the pad. Compact and adjust to bring this to the level of the underside of the paving.
- 5 Replace the paving slabs and ensure that they are well bedded in.
- 6 Place the bench in the desired location and mark through the fixing holes making sure this is done accurately.
- 7 Remove the bench and drill through the paving slabs into the concrete pad below. Drill following fixing manufacturer's instructions to suit the chosen fixing. Choose a fixing which will accept an M8 SS button head bolt, either a mechanical anchor (such as Hilti HSC-IR M8*40) or an internally threaded fixing designed for chemical fixing (such as Hilti HIS-RN M8xL [length to suit]). IMPORTANT, the depth of the hole must be sufficient to allow the fixing to be fully embedded in the concrete rather than partially in the paver and partially in the concrete.
- 8 Insert the fixings into the ground following fixing manufacturer's instructions. Reposition the bench and screw in M8 SS button heads into the 4 no. fixings. Where chemical fixing is used (such as Hilti HIT-HY 150) leave sufficient time to cure before. Tighten the bolts.



Foundations

The seat can be fixed directly to a concrete slab or to concrete pads beneath paving stones. Foundations must be to engineer's specification.



Above, fixing details.

s59.2ms Care and Maintenance Guidelines

The s59.2 seat is constructed from powder coated galvanized steel and iroko hardwood. The materials have been selected for their excellent outdoor durability as well as their aesthetic properties. The timber components have had a micro porous woodstain factory applied as a means of preserving the rich colour of the timber and maximising longevity.

Some care is required to maintain the product's original appearance. The extent to which maintenance is required will depend on a number of factors including environmental conditions, construction activity and level of use.

Maintaining the painted galvanized steel frame

The s64 frame is finished in polyester powder, a plastic coating which is baked onto the components prior to assembly. This is a highly durable finish which will last for many years. To maintain the original appearance of the metalwork it should be cleaned regularly using warm soapy water. Avoid the use of abrasive cleaners as they may damage the surface finish.

Should the paint become chipped or scratched it can be touched up using acrylic based paint. If the damage has penetrated the galvanized coating the area should be cleaned with a wire brush and a zinc rich primer should be applied prior to the top coat. For further advice contact Omos on + 353 45 899802.

Maintaining the timber

Sikkens woodstain coatings have been factory applied to this product to preserve the timber's rich colour. Dirt can be removed using mild detergents. In time re-coating will be required to maintain the original colour of the timber. Omos recommends the use of Sikkens products if and when re-coating is necessary.

If the timber is left untreated, over time it will gradually change to a silvery grey colour. The timber will remain structurally sound without further maintenance.



Above, s59.2ms seat detail.

Wood Finishes

Below shows Iroko timber with factory applied micro-porous stain. This finish offers very good resistance to UV rays and provided the coating surface does not become broken the colour will not fade for several years. The coating is however vulnerable to conditions where high moisture and severe cold persist. Such conditions can cause the coating to blister and lift. Where maintenance is required the surface can be re-coated using a brush on version of the coating. Omos provide maintenance instructions for all products.



Below shows Iroko timber untreated and freshly sanded. The inset image to the right shows untreated Iroko after seven years exposure and no maintenance. When untreated the timber begins to fade within weeks of being exposed to sunlight. After a time it goes silvery grey. Despite the difference in appearance, the timber remains structurally sound. If desired the surface can be 'cut' back' using sand paper to reveal the original colour of the timber.

