

**HÜPER OPTIK®**  
Nano-Ceramic Window Films



The Smarter Choice:  
Nano-Ceramic Films

### HÜPER CERAMIC 15

Visible Light Transmission(%)	15
Visible Light Reflectance (%)	17
Shading Coefficient	0.32
Infrared Rejection (%)	96
UV Light Rejection (%)	99.9
Total Solar Energy Rejected (%)	73
Glare Reduction (%)	84

[www.huperoptikusa.com](http://www.huperoptikusa.com)



Performance data is based on this film being applied to the inside of 3mm clear glass. All data calculated using the definitions and equations in ISO9050 & ASHARE Handbook. The data is subject to variations within industry standards.  
Copyright © 2005 Hüper Optik® USA ([www.huperoptikusa.com](http://www.huperoptikusa.com)), 5821 West Sam Houston Parkway North Suite 400, Houston, TX 77041; phone: 888.296.3456; fax: 832.467.1190



X<sup>3</sup>

Meister Keramische Technologie

HSPEC15