

STONE SPECIFICATION

Mangrove Mt — Buff

INDICATIVE COLOURING AND MARKING FOR THE RANGE



How To Specify:

General:	Sandstone shall be Mangrove Mountain - Buff Sandstone By Gosford Quarries
Stone Type:	Mangrove Mountain Oxidising Stone
Colour:	Gold, Cream, Oxidising sandstone. 'Yellow Block' Characteristics sandstone
Stone Finish:	Diamond Sawn, Gang Sawn, Honed, Rockfaced, Sparrow Pecked & Custom
Sizes:	As Specified by Architect
Fixing:	Adhesive material to be compatible to substrate medium. Stone Cladding above 2.3m in height to be mechanically fixed. Refer to ASAA Natural Stone Design Manual for more info.
Sealing:	Sealer to be specified by Designer or Installer

Typical Technical Specification:

Bulk Density (ASTM C97 -83):	2.4 tonnes/m ³
Absorption by Weight (ASTM C97 -83):	3.9 %
Modulus of Rupture:	9.8 MPa Dry, 2.8 MPa Wet
Compressive Strength: (ASTM C170 -87):	45.6 MPa Dry, 23.2 MPa Wet



The samples illustrated are as accurate as photographic, colour reproduction and printing processes allow. As with all natural materials, some degree of variability can be expected.



70 QUARRY ROAD
SOMERSBY
NSW, 2250

Phone: 02 8585 8282
Fax: 02 9555 4566
sales@gosfordquarries.com.au
gosfordquarries.com.au