



SPECIFICATIONS	UNIT OF MEASURE	VALUE	METHOD OF EVALUATION
CARBON CONTENT	wt. %	>85	TGA, EDX
CNT CONTENT	wt. %	≥75	TEM, TGA
NUMBER OF LAYERS CNT	unit	1-2	TEM
OUTER MEAN DIAMETER CNT	nm	1.8±0.4	RAMAN, TEM
LENGTH OF CNT	µm	>5	AFM
METAL IMPURITIES	wt. %	<15	EDX, TGA



RAMAN SPECTRUM



TGA CURVES



TEM IMAGES



Asia: OCSiAl Asia Pacific
33F Trade Tower WTC, Seoul 135-729,
South Korea
Tel: +81 34 5790 895, +82 50 8113
6959
asiapacific@ocsial.com

Europe: OCSiAl Ltd
207 Regent Street, London W1B 3HH, United Kingdom
Tel: +44 20 3126 4860
Holzhauser Str. 177, Berlin 13509, Germany
Tel: +49 30 4749 4143
europe@ocsial.com

USA: OCSiAl LLC
1804 Embarcadero Rd., Suite 202, Palo
Alto, California 94303, USA
20 S Third St., Suite 210, Columbus,
OH 43215, USA
Tel: +1 415 906 5271
usa@ocsial.com

Russia: OCSiAl.ru LLC
29 Kalanchevskaya Str., bld. 2, Moscow 107078, Russia
Tel: +7 499 653 515
Injenernaya Str., 24, Novosibirsk, 630090
Tel: +7 383 201 8387
russia@ocsial.com