

BRIEF CARD

GHS Brief Card is produced from pure pulp to ensure a paper with consistent quality.

FEATURES & BENEFITS


COATED

- 84 - 87% Brightness - ISO Brightness
- A slightly coated side
- Excellent printability

UNCOATED

- 87 - 88% Brightness - ISO Brightness
- Three types: Regular, High White, Bleach-free
- Machinability and premium convertibility
- Excellent strength and performance in printing
- OBA FREE - Bleach-free. Developed for food contact


END USE APPLICATIONS



Greeting Cards



Photo Albums



Menus



File Folders

Property	Unit	Test Method Reference	Tolerance	Basis Weight							
Basis Weight	g/m ²	ISO 536	±3%	140	160	180	200	230	250	300	
Thickness	µm	ISO 534	±4%	168	192	216	240	275	300	360	
Smoothness	s	ISO 5627	±10	25	25	25	25	25	25	25	
Brightness	%ISO	ISO 2470	±1.5	92	92	92	92	92	92	92	
Opacity	%	ISO 2471	±3	98	98	98	98	98	98	98	
Tensile	MD	kg f/ 15mm	ISO 1924	Min	6.5	7.0	7.5	8.0	9.0	9.5	10.0
	CD				3.0	3.2	3.4	3.5	3.6	3.8	4.0
Moisture	%	ISO 287	±2	6	6	6	6	6	6	6	
Wax Picking	A	T 459	±2	16	16	16	16	16	16	16	
Cobb60 Data	g/m ²	ISO 535	±20	50	50	50	50	50	50	50	

