

FEATURES & BENEFITS

- 100% pure wood pulp
- Neutral, good humidity resistance and can be stored for long time
- Advanced technology, brand-new machinery and full range of product line
- High brightness & whiteness comfortable visual

END USE APPLICATION



Documents



Direct Mail



Letters, Faxes

Property	Unit	Test Method Reference	Basis Weight		
Basis Weight	g/m ²	T410 om-98	70±3	75±3	80±3
Thickness	µm	T411 om-97	86 ~89	93 ~96	103 ~106
Smoothness	sec/10ml	T479 om-91	30±10	30±10	30±10
Brightness	%ISO	ISO 2470-1999	96 ± 1	96 ± 1	96 ± 1
Moisture	%	T412 om-94	4.5 ± 0.5	4.5 ± 0.5	4.5 ± 0.5
Wax Pick	°A	T459 om-93	≥14	≥14	≥14

