

APPLICATION INSTRUCTIONS



HOWARD
CUSTOM TRANSFERS, INC.

HOWARD MULTI-PURPOSE

100% cotton, cotton/poly blends

See next page for low-temperature instructions.



TIME
10-12 seconds



PRESSURE
medium



TEMPERATURE
350°F



PEEL
hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 3-5 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



HOWARD MULTI-PURPOSE

100% poly, spandex, lycra

See previous page for cotton, cotton/poly blends.



TIME

20-25 seconds



PRESSURE

medium



TEMPERATURE

310°F



PEEL

hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5-10 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



HOWARD SUB-LOCK

sublimated garments, 100% polyester



TIME
10 seconds



PRESSURE
medium/firm



TEMPERATURE
270°F



PEEL
cold

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5 seconds. Repeat as necessary

wash instructions

Machine wash garment inside out using COLD water and a mild detergent on a gentle cycle. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



ULTRA STRETCH

**100% cotton, 100% polyester, cotton/poly blends,
lycra, spandex**



TIME

12-14 seconds



PRESSURE

medium



TEMPERATURE

335-340°F



PEEL

cold

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 3 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Lay flat to dry. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



4 COLOR PROCESS

100% cotton, cotton/poly blends

See next page for low-temperature instructions.



TIME

10-12 seconds



PRESSURE

medium



TEMPERATURE

350°F



PEEL

hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 3-5 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



4 COLOR PROCESS

100% poly, spandex, lycra

See previous page for cotton, blends instructions.



TIME

20-25 seconds



PRESSURE

medium



TEMPERATURE

310°F



PEEL

hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5-10 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



GLITTER

100% cotton, cotton/poly blends

For high-gloss finish, cover with Teflon and re-press 5 seconds.



TIME

15 seconds



PRESSURE

firm



TEMPERATURE

350°F



PEEL

hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5-10 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Lay flat to dry. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



VINTAGE WASH

100% cotton, 100% polyester, cotton/poly blends



TIME
10-12 seconds



PRESSURE
firm



TEMPERATURE
350°F



PEEL
hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 3-5 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



HOWARD HOT PEEL

100% cotton

See next page for cotton/poly blends.



TIME

10-12 seconds



PRESSURE

firm



TEMPERATURE

375°F



PEEL

hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5-10 seconds. Repeat as necessary

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



HOWARD HOT PEEL

cotton/poly blend

See previous page for 100% cotton.



TIME

10-12 seconds



PRESSURE

firm



TEMPERATURE

375°F



PEEL

hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 3-5 seconds. Repeat as necessary

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



GLOW IN THE DARK

100% cotton, 100% polyester, cotton/poly blends

For best results, place printed garment in front of fluorescent light to activate glow.



TIME

10-12 seconds



PRESSURE

medium



TEMPERATURE

350°F



PEEL

hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 3-5 seconds.

wash instructions

Machine wash garment inside out using warm water and a mild detergent. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



HOWARD SUPER HOLD 3

100% cotton, 100% polyester, cotton/poly blends,
woven nylon, leather, mesh



TIME
15 seconds



PRESSURE
medium



TEMPERATURE
330°F



PEEL
hot

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5 seconds.

wash instructions

Machine wash garment using warm water and a mild detergent. Tumble dry low. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



BLING

100% cotton, 100% polyester, cotton/poly blends



TIME

15 seconds



PRESSURE

medium



TEMPERATURE

330°F



PEEL

cold

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5 seconds.

wash instructions

Machine wash garment using warm water and a mild detergent. Tumble dry low. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



3M™ REFLECTIVE

100% cotton, 100% polyester, cotton/poly blends



TIME
4 seconds



PRESSURE
medium



TEMPERATURE
320°F



PEEL
cold

Cover with Teflon and press additional 10 seconds.

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5 seconds.

wash instructions

Machine wash garment using warm water and a mild detergent. Tumble dry low. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



STRETCH

100% cotton, 100% polyester, cotton/poly blends, lycra, spandex



TIME

10 seconds



PRESSURE

medium



TEMPERATURE

305°F



PEEL

hot or cold

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 4 seconds.

wash instructions

Machine wash garment using warm water and a mild detergent. Tumble dry low. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



SOLUTIONS OPAQUE

**100% cotton, 100% polyester, cotton/poly blends,
nylon, lycra, waterproof materials**



TIME

5 seconds



PRESSURE

medium



TEMPERATURE

305°F



PEEL

hot

Cover with parchment paper.

Re-apply additional 2 seconds without parchment.

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 4 seconds.

wash instructions

Machine wash garment using warm water and a mild detergent. Tumble dry low. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



PHOTO TRANSFER FOR WHITE

100% cotton, 100% polyester, cotton/poly blends



TIME
20 seconds



PRESSURE
firm



TEMPERATURE
360°F



PEEL
hot

Cut out design leaving 1/8 inch border.
Apply transfer ink side down.

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5 seconds.

wash instructions

Machine wash garment using warm water and a mild detergent. Tumble dry low. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.



PHOTO TRANSFER FOR DARK

100% cotton, 100% polyester, cotton/poly blends



TIME
25 seconds



PRESSURE
medium



TEMPERATURE
365°F



PEEL
hot

Trim around design so there is no border. Peel backing. Position transfer ink side up and cover with parchment.

TIPS/TECHNIQUES

proof

Proof your order before printing on a sellable garment. Using one of the extras included in your shipment, test the transfer on a scrap garment. For multiple tests, cut the extra transfer in half or quartered.

pre-heat

Always pre-heat your garment to remove excess moisture, at least 5 seconds.

wash instructions

Machine wash garment using warm water and a mild detergent. Tumble dry low. Do not bleach. Do not iron on decoration.

shelf life

This product is guaranteed for up to 6 months from the day of production.

