

# AeroAggregates UL-FGA G15

Ultra-Lightweight Foamed Glass Aggregate

## **Density (Unit Weight)**

Uncompacted dry bulk density (ASTM C29/C29M/ AASHTO T 19)<sup>1</sup> 12-15 pcf

Estimated compacted dry density

1.11 Compression Ratio (10% Compaction of Each Lift)
1.25 Compression Ratio (20% Compaction of Each Lift)
15-18.8 pcf
Estimated buoyant unit weight
-15 pcf

## Typical Gradation Characteristics (uncompacted) [ASTM C136/ AASHTO T 27] <sup>1</sup>

D85 2.5" (maximum) 0.375" (minimum)

### **Physical Characteristics**

Moisture	Content
Moistaic	OULICIT

 Volumetric (%)
 0-10 (6% typical)

 Gravimetric (%) [ASTM C566/ AASHTO T 255]¹
 0-60 (25% typical)

 Particle Specific Gravity (AASHTO T 85)
 0.38

 Porosity
 0.5

 1.25 Compression Ratio
 0.38

 Soundness (% Loss)
 0.38

Magnesium Sulfate (ASTM C88/AASHTO T 104¹)

Sodium Sulfate (ASTM C88/AASHTO T 104¹)

3.1- 6.9

Stability

Angle of internal friction – loose 45°
Angle of internal friction – up to 1200 psf (ASTM D3080¹) 55°
Angle of internal friction – up to 3000 psf (ASTM D3080¹) 41°

<sup>&</sup>lt;sup>1</sup>Modified test method due to particle size/density

# **Physical Characteristics (cont.)**

m	n	ш	rı	ŤΙ	$\triangle$	C
	v	u	11	u	$\Box$	C

Clay lumps (ASTM C142)	0
Organic impurities (ASTM C40)	0
Popouts (ASTM C151)	0

Electrical Resistance

Lab (AASHTO T 288) 15,600 ohm-cm

#### **Chemical Characteristics**

Ignition loss (ASTM C114)	0
Sulfates (ppm) [AASHTO T 290]	11
Chlorides (ppm) [AASHTO T 291]	<10
TCLP (SW-846)	Non-leaching

# **Daily Quality Control Testing**

Bulk dry density, maximum [EN 1097-3] <sup>1</sup>	15 pcf
Compressive Strength at 20% Deformation, minimum [EN 1097-11] <sup>1</sup>	15,000 psf

#### **Advantages**

Good Insulator	Capillary Break	Freeze-Thaw Stable	Rodent Resistant
Highly-Permeable	Volume Stable	Non-Flammable	Accelerated Construction

## **Shipping & Handling**

100 CY/Truckload

By shipping up to 100 CY per truckload, we are not only reducing the number of trucks on the road, helping logistics, but we also are reducing the carbon footprint of your aggregate needs.

Material can also be supplied in super sacks for easy placement on sites with confined access.

For more information, please visit aeroaggregates.com or call (833) 261-8499.



<sup>&</sup>lt;sup>1</sup>Modified test method due to particle size/density